

LIST OF PROPERTIES

		P6825
MATERIAL COMPOSITION		
FABRIC		100 % PES / 1100 DTEX
TOTAL WEIGHT	DIN EN ISO 2286/2 1998	900 G/M ²
LACQUERING		1/1
EMBOSSING		GLOSSY
BREAKING STRENGTH WARP	EN ISO 1421/1 1998	4000 N / 5 CM
BREAKING STRENGTH WEFT	EN ISO 1421/1 1998	4000 N / 5 CM
TEAR STRENGTH WARP	DIN 53363 2003	600 N
TEAR STRENGTH WEFT	DIN 53363 2003	500 N
ADHESION	EN ISO 2411 2000	100 N / 5 CM
TEMPERATURE RESISTANCE	DIN EN 1876/2 1198	-30/+70 °C
LIGHT FASTNESS (EXCEPT WHITE AND (HALF-)TRANSPARENT)	ISO 105 B02 1988	7 - 8
FIRE BEHAVIOR	ISO 3795 1989	< 100 MM/MIN
APPLICATION		TRUCK/SIDECURTAIN

All our technical characteristics are indicative

9917 – 300 CM - NOT PRINTED ©



100 % PES
1100 DTEX



900 G/M²



WA: 4000 N / 5 CM - 600 N
WE: 4000 N / 5 CM - 500 N



-30/+70 °C
LIGHT FASTNESS 7 - 8



< 100 MM/MIN

© THIS IS A STANDARD PRODUCT.